

TEST CERTIFICATE

TOPSEAL 200 4mm BLACK

We hereby certify that the information given below is the result of tests carried out on samples of TOPSEAL 200 4mm Black Waterproofing Membranes manufactured in our Dammam factory on 20.07.2026 under production batch no. 11101849, 11101852 and analyzed in our Quality Control department in accordance with *ISO 9001:2015*.

Characteristics	Unit Measure	Test Method	Average Results
1. Thickness	mm	UEAtc	4.01
2. Mass	Kg/m ²	UEAtc	4.85
3. Softening Point	°C	ASTM D-36	157
4. Penetration	dmm.	ASTM D-5	18
5. Tensile Strength			
Longitudinal	N/5cm	UEAtc	936
Transverse	N/5cm	ASTM D-5147	762
6. Elongation at break			
Longitudinal	%	ASTM D-5147	52
Transverse	%	ASTM D-5147	55
7. Tear Resistance			
Longitudinal	N	ASTM D-5147	582
Transverse	N	ASTM D-5147	486
8. Lap Joint Strength			
Longitudinal	N	UEAtc	Same as
Transverse	N	UEAtc	Membrane
9. Heat Resistance	°C	UEAtc	No flow
@ 100 °C			
10. Water Absorption,	%, Wt	ASTM D-5147	0.32
@ 23 °C, 24 Hrs.			
11. Cold Flexibility, - 4	°C	UEAtc	Pass

For
Bitumat Co. Ltd.
Issue date: 02.08.2026.




(Quality Control Manager)

Headquarters: 59th Street, 2nd Industrial City,
P.O. Box 7487, Zip Code: 31462
Dammam, Kingdom of Saudi Arabia
Chamber of commerce: 1848

Jeddah Office: P.O. Box 12605, Zip Code: 21483
Riyadh Office: P.O. Box 12629, Zip Code: 12841

Paid up Capital: SR 60,000,000 - C.R.: 2050014708

T: +966 13 812 1210

T: +966 12 664 4449
T: +966 11 477 0443

www.bitumat.com | info@bitumat.com

المقر الرئيسي: شارع 59، المدينة الصناعية الثانية،
ص.ب 7487، الرمز البريدي 31462
الدمام، المملكة العربية السعودية
غرفة التجارة: 1848

مكتب جدة: ص.ب 12605، الرمز البريدي: 21483
مكتب الرياض: ص.ب 12629، الرمز البريدي: 12841

رأس المال المدفوع: 60,000,000 ريال سعودي - سجل تجاري: 2050014708